

CERAMENT® BONE VOID FILLER

Product Fact Sheet



COMPOSITION:

CERAMENT Powder	Liquid
<p>60 wt% α-calcium sulfate hemihydrate (CaS)</p> <p>40 wt% hydroxyapatite (HA)</p> <ul style="list-style-type: none"> • A calcium phosphate with a chemical and structural similarity to the mineral phase of bone • Osteoconductive, which means it forms a direct bond with osteoblasts that form new bone • Engineered to have a specific size, shape and crystallinity that confers high injectability and slow resorption rate 	<p>Iohexol (CERAMENT C-TRU)</p> <ul style="list-style-type: none"> • Radiocontrast agent with an iodine concentration of 180 mg iodine/mL • Iohexol release is (a) by wash-out of body fluids soaking through micropores, and (b) through calcium sulphate resorption • > 80% is eliminated from the body within 24 hours

TIP EXTENDERS:

11G, 50mm length
 11G, 100mm length
 Tapered tip

SIZE AND ORDER CODES:

Volume	Order code
5mL	A0210-06
10mL	A0210-05
18mL	A0210-10

GMDN code	17751
UMDNS code	37286

Manufacturer:

BONESUPPORT AB
 Scheelevägen 19
 IDEON Science Park
 SE-223 70 Lund
 Sweden

Email: info@bonesupport.com
www.bonesupport.com

REGULATORY INFORMATION:

Regulatory Status

Notified Body: BSI
 Notified Body Number: 2797
 Medical Device Classification: Class III by rule 8 and 13 of the Council Directive 93/42/EEC amended by Directive 2007/47/EC

Intended Use

CERAMENT BONE VOID FILLER is a resorbable ceramic bone graft substitute intended to fill gaps and voids in the skeletal system to promote bone healing. CERAMENT BONE VOID FILLER provides a void/gap filler that during the surgical procedure can augment hardware and bone alignments.

Indications

CERAMENT BONE VOID FILLER is indicated to be placed into bone voids or gaps in the skeletal system, i.e. extremities and pelvis (only during acetabular revision) not intrinsic to the stability of the bony structure. These osseous defects may be:

In skeletally mature patients: spontaneously occurring, surgically created, resulting from traumatic injury to the bone, identified during primary surgery and revision surgery, or osseous defects identified around hardware devices.

Description

CERAMENT BONE VOID FILLER is a fast setting, injectable and moldable ceramic bone graft substitute material intended for bone voids/gaps. The material consists of a powder and a liquid component. The major constituents of the powder are hydroxyapatite and calcium sulfate hemihydrate. The liquid component (C-TRU) contains iohexol as a radio-opacification enhancer. Mixing the components, with the combined mixing injection (CMI) device, results in a viscous material intended to

set ex-vivo or in-vivo. By combining hydroxyapatite and calcium sulfate an optimal balance is achieved between implant resorption rate and bone in-growth rate. Calcium sulfate acts as a resorbable carrier for hydroxyapatite. Hydroxyapatite has a slow resorption rate, high osteoconductivity promoting bone in-growth and gives long term structural support to newly formed bone.

The ceramic bone substitute material is placed into the bone void under visual inspection or under radiographic monitoring during open or percutaneous surgery.

The paste may be injected into the defect, molded by hand and digitally placed into the defect, or used to prepare beads that are placed into the defect. The accompanying device (ID) and Tip Extenders may be used to facilitate the filling of the bone defect.

When fully set in vivo, CERAMENT BONE VOID FILLER is drillable and can be used to augment hardware during the surgical procedure.

Contraindications

- Hypersensitivity to Iohexol or to any of the excipients
- Local infection at the site of implantation
- Pregnancy
- Breastfeeding
- Manifest thyroxicosis

PACKAGING MATERIAL SPECIFICATIONS:

Latex	Not made with natural rubber latex
Animal tissue	Commission regulation No 722/2012 does not apply
Phthalates	Not made with phthalates
Storage conditions	15–30°C / 59–86°F
Shelf-life	48 months
Sterilization	CERAMENT CMI: gamma irradiation CERAMENT C-TRU liquid: steam Complete device: surface sterilized with ethylene oxide

Sterile	Yes
Single Use/disposable	Yes
Sterilization methods:	EO, Steam and Gamma Irradiation
EO residuals	Fulfills ISO 10993-7:2008

Packaging dimensions

37.4cm (l) x 18.65cm (w) x 5.35cm (d)

CERAMENT MATERIAL SPECIFICATIONS:

Setting temperature	<43°C
Initial compressive strength	65–75 MPa (dry conditions), 10–12 MPa (wet conditions)
Initial microporosity	20–40 %
Initial pore size	Average pore size 1 micron

Biocompatibility

The product has been evaluated to be biological safe to use (no unacceptable biological risks have been found). The components of the implantable paste have been used in humans for decades. The plastic components of the product, that come in direct or in indirect contact with the patient, are all of USP Class VI or equivalent. The final product has been extensively tested with biocompatibility in-vitro and in-vivo tests, following the requirements of EN ISO 10993-1.

Handling

- ✓ Injectable
- ✓ Moldable (by hand) – for up to 1 minute max.
- ✓ For use with a bead mold tray (not included in pack)
- ✓ Drillable

Compatibility

- ✓ Autograft, allograft, hardware

